

AMENDMENT UNDER 37 C.F.R. § 1.111

Application Number: 0/694,724

Attorney Docket Number: Q78154

8/1/2008 Please replace the sentence from page 1¹⁵, line 2⁹3, to page 15, line 4¹⁴ with the following amended sentence:

More specifically, a preferable propylene-based polymer composition is one composed of from 40 to 70 % by weight of a propylene-based polymer component (I) which has an intrinsic viscosity $[\eta]^A$, measured in ~~tetralin~~ TETRALIN® (1,2,3,4-tetrahydronaphthalene) at 135 °C, of 5 dl/g or more and a melting peak temperature T_m , measured using a differential scanning calorimeter, of from 130 to 160°C and from 60 to 30 % by weight of a propylene-based polymer component (II) which has an intrinsic viscosity $[\eta]^A$, measured in ~~tetralin~~ TETRALIN® (1,2,3,4-tetrahydronaphthalene) at 135°C, of from 0.8 dl/g to 1.3 dl/g and a melting peak temperature T_m , measured using a differential scanning calorimeter, of from 130 to 165 °C.

Please replace the sentence on page 26, lines 24-26 with the following amended sentence:

Regarding a crystalline polypropylene, the intrinsic viscosity was measured at a temperature of 135°C using TETRALIN® (1,2,3,4-tetrahydronaphthalene) ~~tetralin~~ as a solvent.